

Features

- · Easy to apply
- · Chemically inert
- Waterproof
- · Virtually dust-free
- Meets all of the requirements of the 1990 Clean Air Act
- Is a "Domestic End Product" as defined in the Buy American Act, Title 41 USC 10

Description

TYPE: 1 - Rounds of rods of various diameters intended for use with cold- and hot-applied sealants.

FORM: Round Foam Rod.

TEMPERATURE LIMITS: -45F to +410F.

| Physical Properties | | | | | | |
|----------------------------------|---------------------|----------------------|--|--|--|--|
| Property | Value | ASTM Test Methods | | | | |
| Density lb/ft³ (kg/m³), avg. | 1.3-2.3 (20-37) | D 1622 | | | | |
| Outgassing (No. of Bubbles) | >1 | C 1253 | | | | |
| Compression Recovery, %, min | > 96 | D 5249 | | | | |
| Compression Deflection psi (kPa) | 5.8 (39.9) | D 5249 | | | | |
| Tensile Strength psi (kPa) | 23.5 (162) | D 3575 | | | | |
| Water Absorption (g/cc) | < .03 | C 1016 - Procedure B | | | | |
| Heat Resistance °F (°C) | 410°+5° (200°+2.8°) | D 5249 | | | | |

Benefits

HBR XL limits the depth of the sealant and prevents excessive sealant use. It also helps sealant assume optimum shape factor to prolong sealant service life and acts as a barrier to the flow of sealant through the joint.

Applications

Common applications include, but are not limited to, expansion and contraction joints, curtain walls, construction partitions, parking decks and bridge construction where both cold- and hot-applied sealants are used.

Storage

Store in a well ventilated area. Do not store products in direct sunlight. Keep away from heat sources and open flames.





HBR[®] XL Cross-Linked, Closed Cell Backer Rod



| Product Packaging Information and Recommended Diameter Use for Joint Width | | | | | | | | | |
|----------------------------------------------------------------------------|------------|----------------|-----------------|-------------------|--------------------|--|--|--|--|
| Product | Unit | Roll Length | Unit Weight | Unit Dimension | Joint Dimension | | | | |
| 3/8"(10 mm) | Spool | 3600' (1097 m) | 12 lbs (5.4 kg) | 18" x 18" x 31" | 1/4" (6 mm) | | | | |
| 1/2"(13 mm) | Spool | 2500' (762 m) | 12 lbs (5.4 kg) | 18" x 18" x 31" | 3/8" (10 mm) | | | | |
| 5/8" (16 mm) | Spool | 1550' (472 m) | 12 lbs (5.4 kg) | 18" x 18" x 31" | 1/2" (13 mm) | | | | |
| 7/8" (22 mm) | Spool | 850' (259 m) | 12 lbs (5.4 kg) | 18" x 18" x 31" | 5/8" (16 mm) | | | | |
| 1" (25 mm) | Spool | 550' (168 m) | 12 lbs (5.4 kg) | 18" x 18" x 31" | 3/4" (19 mm) | | | | |
| 1-1/4" (32 mm) | Spool | 400′ (122 m) | 12 lbs (5.4 kg) | 18" x 18" x 31" | 7/8" (22 mm) | | | | |
| 1-1/2" (38 mm) | Cut Length | 550' (168 m) | 18 lbs (8 kg) | 23" x 13" x 75" | 1-1/8" (29 mm) | | | | |
| 2" (51 mm) | Cut Length | 360' (110 m) | 18 lbs (8 kg) | 23" x 13" x 75" | 1-5/8" (41 mm) | | | | |

Joint Preparation and Installation

Just prior to installing HBR XL, clean all joints per the sealant manufacturer's recommendations. Thoroughly remove any concrete form-release agents, curing compound residue, laitance, or any foreign materials. To ensure a good sealant bond, joints must be clean and dry when the new sealant is installed. Air compressors used for this purpose must be equipped with traps for removal of oil and moisture. Install HBR XL at the depth recommended by the sealant manufacturer with a blunt tool.

Size Selection

Proper size selection is important as it controls the depth of the sealant bead. It must be oversized (25-50%) to fit tightly into the joint and function as a bond-breaker to prevent back-side adhesion of the sealant.

Compatibility

Cross-linked polyethlene foam is an inert material; and therefore, it is compatible, both physically and chemically, with virtually all known hot and cold applied sealants including self-leveling types.

Precautions

Do not puncture, over compress or stretch HBR XL during insertion. Tests for outgassing of cold applied sealants shall be made in accordance with ASTM Test Method C 1253. Sealant compatibility should be confirmed by the sealant manufacturer. Compatibility characteristics of sealants in contact with sealant backings can be determined by ASTM Test Method C 1087.

| Distributed by: | | | |
|-----------------|--|--|--|
| | | | |
| | | | |
| | | | |
| | | | |